

Technical Service Report

AWE-13-4343

30.12.13 FR

Att.:

N.V.RUDOLF CHEMIE S.A.,
Jeroen Sobrie

Ref.:

JS/NL/513.074

Company:

VEROSOL FABRICS B.V.

Material:

Metalized Flame Retardant Polyester fabric

Subject:

determination of the antimicrobial effects

Tests and Results

Labor Nr. LF30	Antimicrobial effect Test method: ASTM E 2149-10 mod. (dynamic shake flask test) Incubation: room temperature, 24h Test strain: Staphylococcus aureus (ATCC 6538) Reduction of bacteria - % -	No for external test *)
3) VEROSOL ENVIRO SCREEN original	>99.99	BTS 7297
Lab control fabric	No reduction of bacteria, increase of titre	

*) testing institute BTS:Biotech Testing Services

Note : Presentation of data should not be construed as a public health claim.

Kind regards,

RUDOLF GMBH

i.V. Marianne Frisch

Tel.: +49 8171-53171, Fax: +49 8171-53160